

Claims:

1. A method for producing a bridged polymer membrane, comprising the steps of:
- 5 obtaining a liquid medium comprising a basic polymer having an amino group in a repeating unit, a bridging agent, and a solvent;
shaping the liquid medium into a membrane configuration to obtain a shaped membrane; and
bridging the basic polymer by the bridging agent in the shaped membrane.
-
- 10 2. A method of claim 1 wherein the bridging agent has at least two epoxy groups or isocyanate groups in the molecule thereof.
- 15 3. A method of claim 1 or 2 wherein the liquid medium contains 0.001 to 0.8 mole of the bridging agent per unit of the basic polymer.
- 20 4. A method of claim 1, 2 or 3 wherein the basic polymer is selected from the group consisting of polybenzimidazoles, polyimidazoles, polyvinylimidazoles, and polybenzbisimidazoles.
5. A method of claim 1 further comprising the step of impregnating the basic polymer with a strong acid for providing proton conductivity.
6. A method of claim 1 wherein the basic polymer has a strong acid group in the repeating unit in the basic polymer.
7. A fuel cell comprising a plurality of single cells, each of the single cells comprising a bridged polymer membrane obtained by a method of claim 5 or 6 and a pair of electrodes sandwiching the bridged polymer membrane.
-